



## Test Report

Applicant : MID OCEAN BRANDS B.V.  
UNIT 711-716 7/F TOWER A  
83 KING LAM STREET  
CHEUNG SHA WAN KOWLOON  
HONG KONG

Issue Date : Dec 09, 2025

Attn : JOYCE WONG/DEREK HUI

### SAMPLE DESCRIPTION AS DECLARED

No. of Sample	Several
Fibre Content	-
Material	(A) Rucksack; (B) Sport Bag; (C) Sport Bag (Small)
Finishing	-
End Uses	-
Colour	Black
Style No.	MO2600, MO2758, MO2691
Order No./PO No.	-
Standard	-
Buyer's Name	-
Manufacture's Name	107961
Ref.	-
Date Received/ Date Test Started	Dec 05, 2025

## Conclusions

Test Item	A	B	C
Water Resistance As Received – Rain Test Method	P	P	P

### Note:

Tests presented in this report are conducted as requested by Applicant.

P = Pass      F = Fail      # = No Comment      C = Conform Label  
 N/A = Not Applicable      - = Did Not Perform      \* = See Remark

Approved By:

Intertek Testing Services Hong Kong Limited



Amy Wong

Assistant General Manager

Prepared By: Manny Ching

**Intertek Testing Services Hong Kong Limited**

2/F Garment Centre, 576 Castle Peak Road  
 Kowloon, Hong Kong

Page

3/5

## 1 Water Resistance As Received – Rain Test Method

ISO 22958 - 2005

### Sample A

#### Test Condition

#### Test On Main Body Fabric

	Result	REQ
	Grams Of Water Absorbed (g)	Grams Of Water Absorbed (g)
610 mm, 5 minutes	Neg	Applicant's Requirement: <1g
915 mm, 5 minutes	Neg	Applicant's Requirement: <1g
1220 mm, 5 minutes	Neg	Applicant's Requirement: <1g
1525 mm, 5 minutes	Neg	Applicant's Requirement: <1g
1830 mm, 5 minutes	Neg	Applicant's Requirement: <1g

### Sample B

	Result	REQ
	Grams Of Water Absorbed (g)	Grams Of Water Absorbed (g)
610 mm, 5 minutes	Neg	Applicant's Requirement: <1g
915 mm, 5 minutes	Neg	Applicant's Requirement: <1g
1220 mm, 5 minutes	Neg	Applicant's Requirement: <1g
1525 mm, 5 minutes	Neg	Applicant's Requirement: <1g
1830 mm, 5 minutes	Neg	Applicant's Requirement: <1g

### Sample C

	Result	REQ
	Grams Of Water Absorbed (g)	Grams Of Water Absorbed (g)
610 mm, 5 minutes	Neg	Applicant's Requirement: <1g
915 mm, 5 minutes	Neg	Applicant's Requirement: <1g
1220 mm, 5 minutes	Neg	Applicant's Requirement: <1g
1525 mm, 5 minutes	Neg	Applicant's Requirement: <1g
1830 mm, 5 minutes	Neg	Applicant's Requirement: <1g

---

End of Report

*When a statement of conformity to a specification or standard is provided on test report, the decision rule shall be applied. For details, please refer to the latest version of Intertek's "Decision Rule Information" and is available on Intertek's website. <https://intertekhk.qrd.by/decision-rules-info>. If decision rule already inhered in the requested specification or standard, Intertek's "Decision Rule Information" is not applicable.*

*This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to and subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Intertek is responsible for all the information provided in the reports, except when information is provided by the Client or when the Client requires the item to be tested acknowledging a deviation from specified conditions that can affect the validity of results.*

*The observations and test results in this report are relevant to the sample(s) tested and submitted by client. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. This report does not discharge or release you from your legal obligations and duties to any other person. Only the Client is authorized to permit copying or distribution of this report and the report shall not be reproduced except in full. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.*