

Test Report

Applicant : MID OCEAN BRANDS B.V.
UNIT 711-716, 7/F., TOWER A, 83 KING LAM
STREET, CHEUNG SHA WAN, KOWLOON

Issue Date : Aug 14, 2026

Attn : DEREK HUI

SAMPLE DESCRIPTION AS DECLARED

Sample Description	Ten (10) pairs of submitted samples said to be Oven gloves in Red/Green/White.
Standard	BS EN ISO 21420:2020+A1:2024 / EN ISO 21420:2020+A1:2024 / ISO 21420:2020+A1:2022 EN 407:2020
Size Range	One Size
Style Name	CX1598
Manufacturer	114793
Palm	100% cotton
Back	100% cotton
Cuff	100% cotton
Cuff Binding	100% cotton
Lining	100% cotton
Inner Padding	300gsm 100% polyester
Goods Exported To	Europe
Date of Sample Received	Aug. 03, 2026
Testing Period	Aug. 03, 2026-Aug. 10, 2026
Date Final Information Confirmed / Date Payment Received	--

Approved By: Intertek Testing Services Shenzhen Limited, Guangzhou Branch

Approved By: Intertek Testing Services Shenzhen Limited, Guangzhou Branch



Guiliang Dong
Senior Lab Manager



Rachel Lin
Technical Specialist

Intertek Testing Services Shenzhen Limited, Guangzhou Branch

Room 401/501/601/701-1/801/901/1003, No. 8, East BaoYing Road
Huangpu District, Guangzhou 510730

深圳天祥质量技术服务有限公司广州分公司

广州市黄埔区保盈东路8号401房、501房、601房、701房-1、801房、901房、1003房

Tel: +86 020-28299114 Postcode: 510730

www.intertek.com

1 Cleaning

BS EN ISO 21420:2020+A1:2024 / EN ISO 21420:2020+A1:2024 / ISO 21420:2020+A1:2022, 4.3

As Care Instructions Were Provided, The Relevant Performance-related Tests Of This Document And The Specific Standards Were Performed On The Gloves, Before And After They Had Been Subjected To The Maximum Recommended Number Of Cleaning Cycles.

Wash Condition:

Washing Standard:	ISO 6330:2021
Machine:	Type A
Reagent:	Reference Detergent 3
Washing Procedure:	3N
Bleaching Procedure:	Do not bleach
Drying Procedure:	Do not tumble dry & Line drying
Ironing Procedure:	Do not iron
Professional Textile Care Procedure:	Do not dry clean
Number Of Cycles:	25

2 Glove Design And Construction - General

BS EN ISO 21420:2020+A1:2024 / EN ISO 21420:2020+A1:2024 / ISO 21420:2020+A1:2022, 4.1

Before Washing

Requirement	Yes	No	N/A
The Protector Shall Be Designed And Manufactured So That In The Foreseeable Conditions Of Use, The User Can Perform The Activity As Normally As Possible With An Appropriate Protection. This Document Along With The Appropriate Specific Standards Shall Be Used To Verify This Adequation.	√		
If Required In The Relevant Specific Standard (For Example ISO 16073:2011, 5.7.3), The Glove Shall Be Designed To Minimize The Donning And Doffing Time.	√		
For Reusable Multilayer Protector, The Gloves Shall Be Able To Doffed Without Separation Of The Layers Of The Fingers. When The Protector Construction Includes Seams, The Material And Strength Of The Seams Shall Be Such That The Overall Performance Of The Protector Is Not Significantly Decreased As Required In The Relevant Specific Standards.	√		

After Washing

Requirement	Yes	No	N/A
The Protector Shall Be Designed And Manufactured So That In The Foreseeable Conditions Of Use, The User Can Perform The Activity As Normally As Possible With An Appropriate Protection. This Document Along With The Appropriate Specific Standards Shall Be Used To Verify This Adequation.	√		
If Required In The Relevant Specific Standard (For Example ISO 16073:2011, 5.7.3), The Glove Shall Be Designed To Minimize The Donning And Doffing Time.	√		
For Reusable Multilayer Protector, The Gloves Shall Be Able To Doffed Without Separation Of The Layers Of The Fingers. When The Protector Construction Includes Seams, The Material And Strength Of The Seams Shall Be Such That The Overall Performance Of The Protector Is Not Significantly Decreased As Required In The Relevant Specific Standards.	√		

3 Glove Length

BS EN ISO 21420:2020+A1:2024 / EN ISO 21420:2020+A1:2024 / ISO 21420:2020+A1:2022, 6.1

Before Washing		
Specimen 1	Glove Length:	327 mm
Specimen 2	Glove Length:	330 mm
Specimen 3	Glove Length:	328 mm
After Washing		
Specimen 1	Glove Length:	309 mm
Specimen 2	Glove Length:	305 mm
Specimen 3	Glove Length:	305 mm

4 Contact Heat

EN 407:2020, 6.3 & EN ISO 12127-1:2015

Before Washing		
Test Area:	Palm Of The Glove (No Pretreatment)	
Contact Temperature		Threshold Time
250°C	Specimen 1	20 Seconds
	Specimen 2	20 Seconds
	Specimen 3	21 Seconds
Observation (^): Innermost Layers Of The Glove Showed No Sign Of Melting And Holing.		
Contact Temperature		Threshold Time
350°C	Specimen 1	12 Seconds
	Specimen 2	11 Seconds
	Specimen 3	10 Seconds
Observation (^): Innermost Layers Of The Glove Showed Sign Of Melting And Holing.		

After Washing		
Test Area:	Palm Of The Glove	
Contact Temperature		Threshold Time
250°C	Specimen 1	18 Seconds
	Specimen 2	21 Seconds
	Specimen 3	22 Seconds
Observation (^): Innermost Layers Of The Glove Showed No Sign Of Melting And Holing.		
Contact Temperature		Threshold Time
350°C	Specimen 1	9 Seconds
	Specimen 2	9 Seconds
	Specimen 3	9 Seconds
Observation (^): Innermost Layers Of The Glove Showed Sign Of Melting And Holing.		
Performance Level (^1 & ^2):	2	

Remark: ^ = Innermost Layers Of The Glove Shall Show No Sign Of Melting And Holing.
^1 = The Performance Level Based On The Lowest Of The Single Value.
^2 = For Contact Heat Performance Levels Of 3 Or 4, The Limited Flame Spread Test Shall Be Performed. The Product Shall Reach At Least Level 3 In The Limited Flame Spread Test, Otherwise The Maximum Contact Heat Performance That Shall Be Reported Is Level 2.

Performance Level	Contact Temperature T _c (°C)	Threshold Time t _t (s)
1	100	≥ 15
2	250	≥ 15
3	350	≥ 15
4	500	≥ 15

5 Tear Resistance

EN 407:2020, 6.8

Before Washing		Requirement	Pass/Fail
Test Area:	Outer Layer Of Glove Palm		
Specimen 1:	29 N	≥ 10 N	Pass
Specimen 2:	31 N	≥ 10 N	Pass
Specimen 3:	50 N	≥ 10 N	Pass
Specimen 4:	51 N	≥ 10 N	Pass

After Washing		Requirement	Pass/Fail
Test Area:	Outer Layer Of Glove Palm		
Specimen 1:	27 N	≥ 10 N	Pass
Specimen 2:	19 N	≥ 10 N	Pass
Specimen 3:	29 N	≥ 10 N	Pass
Specimen 4:	21 N	≥ 10 N	Pass

6 pH Value

AS Per BS EN ISO 21420:2020+A1:2024 , 4.2, With Reference To BS EN ISO 3071:2020 For Textile, Potassium Chloride (KCl) Solution Extracted, pH Value Was Measured By pH Meter.

Tested Sample/Component	Result	Requirement's
(1)	5.9	3.5-9.5
(2)	8.0	3.5-9.5
(3)	6.4	3.5-9.5

Temperature Of The Extracting Solution: 23.6 °C

pH Of The Extracting Solution: 5.92

Tested Components: Please See Component List In The Last Section Of This Report.

Conclusion:

Tested Samples/ Tested Components	Test Item/Standard	Result
	BS EN ISO 21420:2020+A1:2024 For pH Value	Pass

7 Azo Colourants Content

With Reference To Test Method: Textile Method (ISO 14362-1: 2017);

Amines Content Was Determined By Gas Chromatography-Mass Spectrometry (GC-MS)

	Forbidden Amine	CAS No.	Result (mg/kg)	
			Method T	
			(1)	
1.	4-Aminodiphenyl	92-67-1	<5	
2.	Benzidine	92-87-5	<5	
3.	4-Chloro-o-toluidine	95-69-2	<5	
4.	2-Naphthylamine	91-59-8	<5	
5.	o-Aminoazotoluene	97-56-3	<5	
6.	2-Amino-4-nitrotoluene	99-55-8	<5	
7.	p-Chloroaniline	106-47-8	<5	
8.	2,4-Diaminoanisole	615-05-4	<5	
9.	4,4'-Diaminodiphenylmethane	101-77-9	<5	
10.	3,3'-Dichlorobenzidine	91-94-1	<5	
11.	3,3'-Dimethoxybenzidine	119-90-4	<5	
12.	3,3'-Dimethylbenzidine	119-93-7	<5	
13.	3,3'-Dimethyl-4,4'diaminodiphenylmethane	838-88-0	<5	
14.	p-Cresidine	120-71-8	<5	
15.	4,4'-Methylene-bis(2-chloroaniline)	101-14-4	<5	
16.	4,4'-Oxydianiline	101-80-4	<5	
17.	4,4'-Thiodianiline	139-65-1	<5	
18.	o-Toluidine	95-53-4	<5	
19.	2,4-Toluylenediamine	95-80-7	<5	
20.	2,4,5-Trimethylaniline	137-17-7	<5	
21.	o-Anisidine	90-04-0	<5	
22. ^a	4-Aminoazobenzene	60-09-3	<5	

Remark: Requirement = 30 mg/kg
Reporting limit = 5 mg/kg

Method T: Direct buffer extraction as per ISO 14362-1: 2017 Section 10.2

Tested Components: Please See Component List In The Last Section of This Report

Conclusion:

Tested Samples/ Tested Components	Standard	Result
	BS EN ISO 21420:2020+A1:2024 Protective Gloves - General requirements and test methods- Azo Colourants Content	Pass

Component List

No.	Component
(1)	White cotton with Green, Red and Black check printing (palm, back, cuff and binding).
(2)	White non-woven fabric (lining).
(3)	White polyester (inner padding).



The statement of conformity in this report is based on the decision rules agreed upon by the Client. Intertek has taken into account the measurement uncertainty calculated by the laboratory. This applies only where no specific decision rules are defined by the Client, regulatory requirements, or standard specifications. Please note that the applied decision rule is applicable solely to numerical test results. For any other cases where specific decision rules have been established by the Client, regulations, or standards, those rules will take precedence over the general guidelines used herein.

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client, Intertek's responsibility and liability are limited to and subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>, Intertek assumes no liability to any party, other than to the Client in accordance with responsible for all the information provided in the reports, except when information is provided the agreement, for any loss, expense or damage occasioned by the use of this report, Intertek is responsible for all the information provided in the report, except when information is provided by the Client or when the Client requires the item to be tested acknowledging a deviation from specified conditions that can affect the validity of results.

All samples information provided in this report was submitted by the Client. The Client is solely responsible for the accuracy and completeness of the samples and associated information. The observations and test results in this report are relevant to the sample(s) tested and submitted by client, The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. This report does not discharge or release you from your legal obligations and duties to any other person. Only the Client is authorized to permit copying or distribution of this report and the report shall not be reproduced except in full, Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek, This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.