





TEST REPORT

Reference No	:	WTF21F03017575C

Applicant: Mid Ocean Brands B.V.

Address : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon,

Hong Kong

Manufacturer..... : 106613

Sample Name : Table set

Model No.....: IT1911

1907/2006 and the amendment No. 552/2009, No. 494/2011, No.

835/2012 and (EU) 2016/217

2) Determination of specified Phthalates content according to Annex XVII Items 51 & 52 of the REACH Regulation (EC) No. 1907/2006

& Amendment No. 552/2009 & No. 2018/2005

3) Determination of specified Polycyclic Aromatic Hydrocarbons (PAHs) content in submitted sample in accordance with Entries 50 of Annex XVII of REACH Regulation (EC) No 1907/2006 and its

amendment Regulation (EU) No 1272/2013.

4) Determination of Benzene content in the submitted sample in accordance with Annex XVII Entries 5 of the REACH Regulation (EC) No. 1907/2006 and the Amendment (EU) No. 2015/1494

5) As specified by client, determination of the released formaldehyde

content in submitted sample

Test Method: Please refer to next page (s)

Test Conclusion : Please refer to next page (s)

Date of Receipt sample..... : 2021-03-09

Date of Test 2021-03-09 to 2021-03-15

Date of Issue: 2021-03-15

Test Result: Please refer to next page (s)

Note : As specified by client, only test the designated sample.

Remarks: The results shown in this test report refer only to the sample(s) tested; this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver.

If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.

Prepared By:

Waltek Testing Group (Foshan) Co., Ltd..

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by: Approved by:

Rena.Chen / Project Engineer Swing.Liang / Technical Manager

Waltek Testing Group (Foshan) Co., Ltd. http://www.waltek.com.cn



Test Result:

1) Cadmium (Cd)

Test Method: With reference to IEC 62321-5:2013, the analysis was performed by ICP-OES.

Test Item	LOQ	Results (mg/kg)				
	(mg/kg)	No.1	No.3	No.4		
Cadmium(Cd)	2	ND ND	ND -	ND ND		
Conclusion		Pass	Pass	Pass		

Note:

- (1) mg/kg = milligram per kilogram
- (2) ND = Not Detected (lower than LOQ)
- (3) LOQ = Limit of quantitation
- (4) Limit of Cadmium according to REACH regulation Annex XVII Item 23 (EC) No. 1907/2006 and the amendment No. 552/2009, No. 494/2011 and No. 835/2012 and (EU) 2016/217.

Category	Limit (mg/kg)
Wet paint	100
Surface coating	1000
Plastic	100
Metal parts of jewellery and hair accessories	100



2) Phthalates

Test Method: With reference to EN14372:2004, by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Test Items	LOQ	MUTER ANTIES	Limit		
	(%)	No.1	No.3	No.4	(%)
Benzyl butyl phthalate (BBP)	0.005	ND	, ND	ND	NICE WALL
Di (2-ethyl hexyl)- phthalate (DEHP)	0.005	ND	ND	ND	sum of four
Dibutyl phthalate (DBP)	0.005	ND	ND	ND ND	phthalat es < 0.1
Diisobutyl phthalate (DIBP)	0.005	ND	ND A	ND ND	
Diisodecyl phthalate (DIDP)	0.01	ND	ND	ND	sum of
Diisononyl phthalate (DINP)	0.01	ND *	ND ND	ND	three phthalat
Di-n-octyl phthalate (DNOP)	0.005	ND	ND	ND	es < 0.1
Conclusion	- 10th - 15	Pass	Pass	Pass	

Note:

DBP= Dibutyl phthalate
DINP= Di-isononyl phthalate

BBP= Benzyl butyl phthalate DNOP= Di-n-octyl phthalate DEHP= Bis-(2-ethylhexyl)- phthalate

DIDP= Di-isodecyl phthalate

- DIBP= Diisobutyl phthalate

 (1) % = percentage by weight
- (2) ND = Not detected or Less than the method detection limit
- (3) LOQ = Limit of quantitation
- (4) "<" = less than
- (5) The above limit was quoted according to Annex XVII Items 51 & 52 of the REACH Regulation (EC) No. 1907/2006 & Amendment No. 552/2009 & No. 2018/2005 (formerly known as Directive 2005/84/EC) for phthalate content in toys and child care articles.

3 (3)



3) Polycyclic Aromatic Hydrocarbons (PAHs)

Test Method: With reference to AFPS GS 2019:01 PAK method, analysis was performed by Gas Chromatographic Mass Spectrometry (GC-MS).

Test Items	Amerit	18th 1	Results	100	411	
	Unit	No.1	No.3	No.4	LOQ	Limit
Benzo(a)anthracene (BaA)	mg/kg	ND	ND	ND	0.2	0.5
Chrysene (CHR)	mg/kg	ND	ND	ND	0.2	0.5
Benzo[b]fluoranthene (BbFA)	mg/kg	ND	ND	ND	0.2	0.5
Benzo[k]fluoranthene (BkFA)	mg/kg	ND	ND	ND	0.2	0.5
Benzo(a)pyrene (BaP)	mg/kg	ND	ND	ND	0.2	0.5
Dibenzo[a,h]anthracene (DBAhA)	mg/kg	ND	ND	ND N	0.2	0.5
Benzo[j]fluoranthene (BjFA)	mg/kg	ND	ND	ND OF	0.2	0.5
Benzo[e]Pyrene (BeP)	mg/kg	ND	ND	ND	0.2	0.5
Conclusion	20 2	Pass	Pass	Pass	RITE WILL	24/16

Note:

- (1) ND = Not Detected or lower than limit of quantitation
- (2) mg/kg=milligram per kilogram=ppm
- (3) LOQ = Limit of quantitation
- (4) As per Entries 50 of Annex XVII of REACH Regulation (EC) No 1907/2006 and its amendment Regulation (EU) No 1272/2013, Articles shall not be placed on the market for supply to the general public, if any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use, contain more than 1 mg/kg (0,0001 % by weight of this component) of any of the listed PAHs.
- (5) As per Entries 50 of Annex XVII of REACH Regulation (EC) No 1907/2006 and its amendment Regulation (EU) No 1272/2013, Toys, including activity toys, and childcare articles, shall not be placed on the market, if any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use, contain more than 0,5 mg/kg (0,00005 % by weight of this component) of any of the listed PAHs.



4) Benzene

Test Method: With reference to US EPA 3550C:2007& US EPA 8270D: 2014, analysis was performed by GC-MS

Test Item LOQ (mg/kg)	LOQ		Limit		
	(mg/kg)	No.1	No.3	No.4	(mg/kg)
Benzene*	1	ND	ND W	ND	5
Conclusion	Mrs Mrs.	Pass	Pass	Pass	WITE - WI

Note:

- (1) mg/kg = milligram per kilogram
- (2) ND = Not Detected (lower than LOQ)
- (3) LOQ = Limit of quantitation
- (4) As per Annex XVII Items 5 of the REACH Regulation (EC) No. 1907/2006 and the Amendment (EU) No. 2015/1494, benzene shall not be used in toys or parts of toys where the concentration of benzene in the free state is greater than 5 mg/kg (0,0005 %) of the weight of the toy or part of toy.
- (5) The testing item marked with "*" do not been accredited by CNAS

5) Formaldehyde

Test Method: With reference to EN717-3:1996, analysis was performed by UV-VIS

Test Item		Result	" ("In" 1	Client's Limit
	Unit	No.2	LOQ	
Formaldehyde (CH ₂ O)	mg/kg	28	10	80
Conclusion	in mi me	Pass	et Jet - Ji	- CLEEK

Note:

- ND = Not Detected or lower than limit of quantitation
- mg/kg =milligram per kilogram=ppm
- LOQ = Limit of quantitation

Test Specimen Description:

No.1: White coating

No.2: Brown wood without white coating

No.3: Black plastic handle No.4: Black soft plastic ball Reference No.: WTF21F03017575C

Sample photo:












Photographs of parts tested:



===== End of Report =====