



TEST REPORT

Reference No. WTF21F09092925C

Applicant Mid Ocean Brands B.V.

Address 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon,

Hong Kong

Manufacturer..... 109328

Sample Name..... Health bracelet (smart watch)

Model No. : MO9771

Test Requested.....: 1) Determination of specified Phthalates content according to Annex

XVII Items 51 & 52 of the REACH Regulation (EC) No. 1907/2006

& Amendment No. 552/2009 & No. 2018/2005

2) Determination of specified Polycyclic Aromatic Hydrocarbons (PAHs) content in submitted sample in accordance with Entries 50 of Annex XVII of REACH Regulation (EC) No 1907/2006 and its

amendment Regulation (EU) No 1272/2013.

3) Nickel content requirement in Annex XVII Item 27 of the REACH Regulation (EC) No. 1907/2006 & amendment No.552/2009 (formerly known as Directive 94/27/EC and 2004/96/EC)

4) Determination of Benzene content in the submitted sample in accordance with Annex XVII Entries 5 of the REACH Regulation

(EC) No. 1907/2006 and the Amendment (EU) No. 2015/1494

Test Method Please refer to next page (s)

Test Conclusion Please refer to next page (s)

Date of Receipt sample....: 2021-09-03

Date of Test..... 2021-09-03 to 2021-09-27

Date of Issue 2021-09-29

Test Result..... Please refer to next page (s)

Note: As specified by client, only test the designated sample.

Remarks:

The results shown in this test report refer only to the sample(s) tested; this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver.

If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.

Prepared By:

Waltek Testing Group (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China

E-mail:info@waltek.com.cn Fax:+86-757-23811381 Tel:+86-757-23811398

Compiled by: Approved by:

Rena.Chen / Project Engineer Swing.Liang / Technical Manager

Waltek Testing Group (Foshan) Co., Ltd. http://www.waltek.com.cn





Test Result:

1) Phthalates

Test Method: With reference to EN14372:2004, by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Test Items	LOQ	Results (%)	Limit	
	(%)	No.1	(%)	
Benzyl butyl phthalate (BBP)	0.005	IT ND IT	me in in	
Di (2-ethyl hexyl)- phthalate (DEHP)	0.005	MD TO	sum of four	
Dibutyl phthalate (DBP)	0.005	ND	phthalates < 0.1	
Diisobutyl phthalate (DIBP)	0.005	IND WILL	Mright Mur. A	
Diisodecyl phthalate (DIDP)	0.01	ND ND	sum of three phthalates < 0.1	
Diisononyl phthalate (DINP)	0.01	ND W		
Di-n-octyl phthalate (DNOP)	0.005			
Conclusion	ality Mar a	Pass	at at - let	

Note:

DBP= Dibutyl phthalate

BBP= Benzyl butyl phthalate

DEHP= Bis-(2-ethylhexyl)- phthalate

DIDP= Di-isodecyl phthalate

DIDP= Di-isodecyl phthalate

(1) % = percentage by weight

DIBP= Diisobutyl phthalate

- (2) ND = Not Detected or lower than limit of quantitation
- (3) LOQ = Limit of quantitation
- (4) "<" = less than
- (5) The above limit was quoted according to Annex XVII Items 51 & 52 of the REACH Regulation (EC) No. 1907/2006 & Amendment No. 552/2009 & No. 2018/2005 (formerly known as Directive 2005/84/EC) for phthalate content in toys and child care articles.



2) Polycyclic Aromatic Hydrocarbons (PAHs)

Test Method: With reference to AFPS GS 2019:01 PAK method, analysis was performed by Gas

Chromatographic Mass Spectrometry (GC-MS).

Test Items	Unit	Results	LOQ	Limit
		No.1	27, 22,	
Benzo(a)anthracene (BaA)	mg/kg	ND	0.2	1.0
Chrysene (CHR)	mg/kg	ND ND	0.2	1.0
Benzo[b]fluoranthene (BbFA)	mg/kg	ND	0.2	1.0
Benzo[k]fluoranthene (BkFA)	mg/kg	ND ND	0.2	1.0
Benzo(a)pyrene (BaP)	mg/kg	ND	0.2	1.0
Dibenzo[a,h]anthracene (DBAhA)	mg/kg	ND	0.2	1.0
Benzo[j]fluoranthene (BjFA)	mg/kg	ND WILL	0.2	1.0
Benzo[e]Pyrene (BeP)	mg/kg	ND	0.2	1.0
Conclusion	LIER WIFE	Pass	7420	- J

Note:

- (1) ND = Not Detected or lower than limit of quantitation
- (2) mg/kg=milligram per kilogram=ppm
- (3) LOQ = Limit of quantitation
- (4) As per Entries 50 of Annex XVII of REACH Regulation (EC) No 1907/2006 and its amendment Regulation (EU) No 1272/2013, Articles shall not be placed on the market for supply to the general public, if any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use, contain more than 1 mg/kg (0,0001 % by weight of this component) of any of the listed PAHs.
- (5) As per Entries 50 of Annex XVII of REACH Regulation (EC) No 1907/2006 and its amendment Regulation (EU) No 1272/2013, Toys, including activity toys, and childcare articles, shall not be placed on the market, if any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use, contain more than 0,5 mg/kg (0,00005 % by weight of this component) of any of the listed PAHs.



3) Nickel release

Test method: With reference BS EN1811: 2011+A1:2015, Nickel content was determined by Inductively Coupled Argon Plasma Spectrometry

Item No. Sample Area (cm²)	Volume of Test	Nickel release (μg/cm²/week)			Conclusion		
	Solution(ml)	Trial 1	Trial 2	Trial 3	Average	- 15 13	
No.2	14.00	10	ND	ND	ND	ND	Pass
No.3	21.42	10	ND	ND	ND	ND	Pass

Note:

- (1) μg/cm²/week = microgram per square centimetre per week
- (2) Limit of quantitation = 0.05 μg/cm²/week
- (3) ND = Not Detected or lower than limit of quantitation
- (4) Interpretation of test results:

et let let let with anitet	Nickel Release(μg/cm²/week)		
Type of sample	Pass	Fail	
Other components in direct and prolonged contact with the skin	et mit <0.88 tet mite	≥0.88	
Post assemblies and body piercings (Post assemblies which are inserted into pierced parts of the human body)	<0.35	≥0.35	

4) Benzene

Test Method: With reference to US EPA 3550C:2007& US EPA 8270D: 2014, analysis was performed by GC-MS

Tracked the title	LOQ	Results (mg/kg)	Limit (mg/kg)	
Test Item	(mg/kg)	No.1		
Benzene*	LITE OF THE WALL	ND	5 (1)	
Conclusion	A LE TEN STEEL IS	Pass	2/4 1/1 2/	

Note:

- (1) mg/kg = milligram per kilogram
- (2) ND = Not Detected (lower than LOQ)
- (3) LOQ = Limit of quantitation
- (4) As per Annex XVII Items 5 of the REACH Regulation (EC) No. 1907/2006 and the Amendment (EU) No. 2015/1494, benzene shall not be used in toys or parts of toys where the concentration of benzene in the free state is greater than 5 mg/kg (0,0005 %) of the weight of the toy or part of toy.
- (5) The testing item marked with "*" do not been accredited by CNAS

Test Specimen Description:

No.1: Black plastic band No.2: Silvery metal sheet


No.3: Silvery metal buckle



Sample photo:



Photographs of parts tested:



===== End of Report =====

Waltek Testing Group (Foshan) Co., Ltd. http://www.waltek.com.cn

